



WestPine



GoldPlus MDF Specifications

Imperial

	5/16 - 1/2"	9/16" – 3/4"
Density	46.5 pcf	46.5 pcf
Internal Bond	110 psi	110 psi
Modulus of Rupture	4,500 psi	4,500 psi
Modulus of Elasticity	400,000 psi	400,000 psi
Screw Holding Face	350 lbs	325 lbs
Screw Holding Edge	n/a	300 lbs
Thickness Swell	0.063 in	9%
Maximum Linear Expansion & Contraction	0.3 %	0.3 %
Thickness Tolerance	±0.005 in	±0.005 in

Metric

	9mm – 12mm	14mm – 19mm
Density	745 kg/m ³	745 kg/m ³
Internal Bond	0.83 N/mm ²	0.83 N/mm ²
Modulus of Rupture	31.0 N/mm ²	31.0 N/mm ²
Modulus of Elasticity	2758 N/mm ²	2758 N/mm ²
Screw Holding Face	1557 N	1446 N
Screw Holding Edge	n/a	1334 N
Thickness Swell	1.6 mm	9%
Maximum Linear Expansion & Contraction	0.3 %	0.3 %
Thickness Tolerance	±0.127 mm	±0.127 mm

Other Characteristics

1. Moisture content: Average moisture content of finished panels as shipped is 4-8%.
2. Formaldehyde emissions: WestPine GoldPlus MDF is CARB Compliant for Phase 2 (complies with CCR 93120.2).
3. Surface Burning Characteristics: Testing done on WestPine MDF show material being Class 3 or C in accordance with ULC Standard CAN/ULC-S102 and ASTM E-84.
4. WestPine MDF is certified with:
 - 1) Composite Panel Association's Environmentally Preferable Product Grademark Program.
 - 2) Scientific Certification Services
 - 3) Forest Stewardship Council for Chain of Custody Certification (FSC-STD-40-004 v2-0) and the Standard for Company Evaluation for Controlled Wood (FSC-STD-40-005 v2-1)
5. Standard finish on all panels is 150 grit.
6. Finished sizes available:
Width 45" to 62"
Length 72" to 205"
7. All physical property values represent the compiled average of quality assurance testing conducted on WestPine MDF. WestPine MDF complies with ANSI A208.2 – 2009 using the prescribed test methods in ASTM D-1037.
8. WestPine MDF is manufactured from 100% Western white softwoods. Appearance is a consistent light sandy color.